

Gokin

TOPCon Bifacial Module with Dual Glass

GK-4-66HTBD | Half-cut | 132cells

590-620W

23.0%

Module Efficiency up to

≤1% First-year Degradation

≤0.4% Annual Degradation



High Efficiency

Module efficiency up to 23.0% based on N-Type wafer and TOPCon technology



Anti-degradation

Unsusceptible to LID, LeTID and less annual degradation due to special characteristics of N-Type



Excellent Energy Yield


More power output in field operation due to better thermal behaviors, weak-light performance and bifaciality



Quality Guarantee

High module quality ensures long-term reliability

Linear Performance Warranty



At least 99% of nominal power during first year;
Thereafter max.0.4% degradation per year;
At least 87.4% of nominal power up to 30 years.




IEC 61215(2021) / IEC 61730(2023)
ISO 9001: 2015: ISO Quality Management System
Anti-PID / Ammonia / Salt-mist / Dust and sand

- Operating Temperature **-40°C ~ +85°C**
- Power Tolerance **0~+5W**
- Junction Box **IP68**
- NOCT **45±2°C**
- Maximum Series Fuse Rating **35A**
- Bifacial Factor **80±5%**
- Maximum System Voltage **1500V(IEC)**


Mechanical Parameters

Cell Type	TOPCon
No. of cells	132 (2×66)
Output Cables	TüV 1×4mm ²
	(+)300mm,(-)200mm in length or customized length
Glass	Front: 2.0mm, AR-coating, semi-tempered
	Rear: 2.0mm, semi-tempered
Frame	Anodized aluminum alloy frame
Weight	32.4 kg (71.43 lbs)
Dimension	2382×1134×30mm
Packaging	37 pcs per pallet
	148 pcs per 20' HC, 740 pcs per 40' HC
Protection Class	Class II

Electrical Performance



Engineering Drawings



Electrical Characteristics (STC Test)

Module Type	GK-4-66HTBD-590M		GK-4-66HTBD-595M		GK-4-66HTBD-600M		GK-4-66HTBD-605M		GK-4-66HTBD-610M		GK-4-66HTBD-615M		GK-4-66HTBD-620M	
	STC	NOCT												
Maximum Power (Pmax/W)	590	447	595	450	600	454	605	458	610	462	615	466	620	469
Open-circuit Voltage (Voc/V)	47.32	44.81	47.49	44.96	47.66	45.16	47.83	45.28	48.00	45.49	48.17	45.65	48.34	45.81
Short-circuit Current (Isc/A)	15.79	12.73	15.86	12.80	15.93	12.86	16.00	12.92	16.07	12.96	16.14	13.02	16.21	13.16
Maximum Power Voltage (Vmp/V)	39.67	37.55	39.81	37.65	39.95	37.78	40.09	37.91	40.22	38.06	40.35	38.16	40.48	38.31
Maximum Power Current (Imp/A)	14.88	11.90	14.96	11.97	15.03	12.03	15.10	12.08	15.18	12.16	15.25	12.20	15.33	12.27
Module Efficiency (%)	21.8		22.0		22.2		22.4		22.6		22.8		23.0	

- 1、STC: Irradiance 1000W/M², Cell Temperature 25°C, AM=1.5
- 2、NOCT: Irradiance 800W/M², Ambient Temperature 20°C, AM=1.5, Wind Speed 1M/S

Different Rearside Power Gain (Reference to 605W)

Rearside Power Gain	5%	10%	20%
Maximum Power at STC (Pmax)	635.3	665.5	726.0
Open-circuit Voltage (Voc/V)	47.8	47.8	47.8
Short-circuit Current (Isc/A)	16.8	17.6	19.2
Maximum Power Voltage (Vmp/V)	40.1	40.1	40.1
Maximum Power Current (Imp/A)	15.9	16.6	18.1
Module Efficiency (%)	23.5	24.6	26.9

Temperature Ratings (STC)

Temperature coefficient of Isc +0.045%/°C

Temperature coefficient of Voc -0.25%/°C

Temperature coefficient of Pmax -0.29%/°C

Mechanical Loading

Front Side Maximum Static Loading 5400Pa

Rear Side Maximum Static Loading 2400Pa

Hailstone Test 25mm hailstone at 23m/s

